

HARRISON WIPES				Item Name : Steadfast White 80gsm					
Composition : 70% Woodpulp + 30% Spunbond				Appearance : White Square Pattern					
Lot No : N/A				Test Date: 25 th December 2018					
Test Items		Unit	Standard	Roll Average			Test No	Test Method	
				Avg.	Min.	Max.			
Basis Weight		g/m ²	80 ± 3.3	78.4	---	---	8	EDANA 40.3-90 (25*20 cm ²)	
Thickness		mm	0.42 ± 0.03	0.42	---	---	8	FZ/T 60004-91 20gf/cm ² ,15.2cm ²	
Tensile Strength at Break	MD	Kg/50 mm	5.0 ↑	7.7	---	---	4	EDANA 20.2-89 Test Speed : 300mm/min Grip Distance : 100mm Specimen Width : 50mm	
	CD		3.0↑	4.6	---	---	4		
Elongation at Break	MD	%	60 ↓	54.5	---	---	4		
	CD		150 ↓	111.5	---	---	4		
Absorption Capacity		%	350 ↑	560	---	---	4		ISO 9073 - 6:2000
Speed of Absorbability		cm/30s	3.5 ↑	5.3	---	---	4		Corporation Standard
Remarks:									