

DATA SHEET

Film consisting of a 60-µm, transparent, cast PVC containing antimicrobial agents and coated with a pressure-sensitive acrylic adhesive. Matt surface finish. Intended for antimicrobial protection of surfaces in areas that require a high level of hygiene.

Active strains (according to ISO 22196):

Reducing > 99.99 % of bacteria ascertained for:

- Escherichia coli,
- Salmonella (Salmonelle enterica),
- Listeria (Listeria monocytogenes),
- Golden staph (Staphylococcus aureus),
- Methicillin-resistant Staphylococcus aureus (MRSA),
- Pseudomonas aeruginosa.

Antiviral activity on the Human coronavirus HCoV-229E strain (according to the ISO 21702 standard):

- •94.99 % after a contact time of 15 min.,
- •99.87 % after a contact time of 60 min.

FILM FEATURES:

Indicative value

• Thickness (µm): 60

<u>Average values</u>

• Tensile strength (N/25 mm): min. 15

• Elongation at break (%): min. 100

• Shrinkage 168 hours at 70 °C (158 °F) (mm): < 0.8



2 Marples Way, Havant, Hampshire. PO9 1UH T. 023 9248 9939

E. help@workplace-infection-control.co.uk



LINER:

- Silicone-coated PE paper
- Stable under hygrometric variations.

ADHESIVE PROPERTIES:

(Measured average values at publication of the technical data sheet)

	<u>Average values</u>
 Peel strength test 180° on glass (N/25 mm): 	
after 20 minutes of application	15
after 24 hours of application	17
• Initial tack (N/25 mm):	20
• Release (N/25 mm):	0.5

• Resistance to solvents: the adhesive is resistant to most chemicals.

ADHESIVE:

- Solvent-based acrylic adhesive.
- Immediate and permanent adhesion.

STORAGE:

Shelf life (before application):

The shelf life of this film is 1 year when stored in its original packaging in a dust-free environment at a temperature ranging from +15 $^{\circ}$ C to +25 $^{\circ}$ C (+59 $^{\circ}$ F to +77 $^{\circ}$ F) with relative humidity of 50 $^{\circ}$ %.

DURABILITY:

- Vertical indoor exposure: up to 5 years (in areas not subject to frequent handling or high visitor frequency).
- A film applied in areas of frequent handling (e.g.: handles) or high visitor frequency will be subject to repeated abrasion which will reduce its durability (change of appearance, lifting, etc.). The film durability depends on the intensity and frequency of the mechanical stress to which it is exposed.



2 Marples Way, Havant, Hampshire. PO9 1UH

T. 023 9248 9939

E. help@workplace-infection-control.co.uk

W. www.workplace-infection-control.co.uk



USER INSTRUCTIONS:

- Under normal usage conditions, harmless when in contact with human skin (skin compatibility study carried out under dermatological control). It has no allergenic or irritant potential.
- Active compound: silver ions, < 0.3 % w/w of the entire product.
- Antimicrobial activity maintained after 365 cleanings with water, alcohol, chlorine bleach and Aniosurf® (respect the dilution recommended by the manufacturer).
- The film can be cleaned/disinfected by all conventional cleaning methods, using nonabrasive accessories, cleaning products, detergents or products currently used in healthcare environments.
- Only apply the film to areas that will not be in direct contact with unpackaged food.
- Suitable for application to regular or irregular surfaces.
- Recommended minimum application temperature: +10 °C (+50 °F).
- \bullet Operating temperature range: from -40 °C to +90 °C (-40 °F to +194 °F).
- In the case of an already painted substrate, self-adhesive media must only be applied to undamaged original paintwork. If the paintwork is not original and/or damaged, the application and the removal are at the judgement and risk of the installer.